



TECHNOLOGY MAKES LIFE BETTER

安徽省蚌埠市高新区兴中路 985 号日月科技园

电话: 86-552-3827158

传真: 86-552-3822922

安徽艾约塔硅油有限公司

Iota Corporation Ltd.

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 86-552-3827158

Fax: 86-552-3822922

IOTA BJ1000 Phenyl Silicone Oils

Product description

IOTA BJ1000 Silicone fluid is a clear, colorless, and odorless polydimethylsiloxane with a high proportion of phenyl groups.

Application

- heat transfer fluid
- pressure transfer fluid
- dielectric in capacitors and transformers
- base fluid of heat resistant lubricants

For practical purposes, the useful temperature range of IOTA BJ1000 is between -35 °C and +200 °C. However, this presupposes that heat-stressing of the fluid occurs under "chemically pure" conditions.

Even trace amounts of acids, alkalis, mineral oils, organometallic compounds, metal salts or metal oxides can seriously reduce the service life.

The flash point of the silicone fluid may be changed by heat-stressing. It is therefore particularly important in open systems to check the flash point at least once a year and more often if operating conditions demand.



TECHNOLOGY MAKES LIFE BETTER

安徽省蚌埠市高新区兴中路 985 号日月科技园

电话: 86-552-3827158

传真: 86-552-3822922

安徽艾约塔硅油有限公司

Iota Corporation Ltd.

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 86-552-3827158

Fax: 86-552-3822922

Storage

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Product data

Typical general characteristics	Inspection Method	Value Appearance
		clear, colorless
Viscosity, dynamic at 25 °C		900-1300 mPa.s
Refractive index (25°C)	DIN 51423	approx.1.51
Density at 25 °C	DIN 51757	approx.1.09 g/cm ³
Volatility	5g/4h/250°C	< 1.0 %
Thermal conductivity at 50 °C		approx.0.14 Wm ⁻¹ K ⁻¹
Specific heat at 25 °C		approx.1.46 Jg ⁻¹ K ⁻¹
Coefficient of thermal expansion at 0 -180 °C		85 - 82 x 10 ⁻⁵ mLmL ⁻¹ K ⁻¹



TECHNOLOGY MAKES LIFE BETTER

安徽省蚌埠市高新区兴中路 985 号日月科技园

电话: 86-552-3827158

传真: 86-552-3822922

安徽艾约塔硅油有限公司

Iota Corporation Ltd.

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 86-552-3827158

Fax: 86-552-3822922

Dielectric constant at 25°C and 100 Hz		approx.2.9
Dielectric strength		approx.20 kVmm ⁻¹
Flash point	ISO 2592	approx.280 °C
Ignition temperature (liquids)	DIN 51794	> 400 °C